

ARMY RESEARCH LABORATORY



Plastic Fins for Kinetic Energy (KE) Penetrators

by Mark L. Bundy

ARL-TR-1267

December 1996

19970210 005

Approved for public release; distribution is unlimited.

DTIC QUALITY INSPECTED 1

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer need. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-1267

December 1996

Plastic Fins for Kinetic Energy (KE) Penetrators

Mark L. Bundy

Weapons and Materials Research Directorate, ARL

Abstract

Most conventional sub-caliber long rod penetrators maintain flight stability by using near-full-caliber hardcoated aluminum fins that extend from the base end of the projectile. Prior to launch, these fins are buried within the propellant bed of the ammunition cartridge case. During launch, the fins are subjected to high propellant gas temperature and pressure, as well as propellant grain impacts. This thermally abrasive in-bore environment can remove pieces of the fin's hardcoat, thus exposing the aluminum substrate to temperatures far beyond its melting point. Thermal erosion of the fin degrades projectile stability and accuracy. Thus, the U.S. Army is exploring more effective thermal coatings and/or substitute fin materials to replace hardcoated aluminum. The use of plastics is one alternative. This report will document some of the successes and failures of plastic fin assemblies on kinetic energy (KE) penetrators. For example, it was found that fins made from some plastics incur less in-bore thermal damage than hardcoated aluminum. On the other hand, it appears that plastic fins, at least relatively thin plastic fins, are susceptible to mechanical failure out of bore if they traverse the reverse muzzle gas flow at all but small yaw angles. Nonetheless, there appears to be design latitude for a plastic fin assembly that would be lighter in weight and more erosion resistant than the current hardcoated aluminum fin.

TABLE OF CONTENTS

LIST OF FIGURES	iii
LIST OF TABLES	v
1. INTRODUCTION	1
2. TEST AND EVALUATION PROCESS	2
2.1 Static Firing	2
2.2 Dynamic Firing	4
3. COMPOSITION AND DESIGN	5
3.1 Materials	5
3.1.1 Short fiber-filled and unfilled plastics	6
3.1.2 Long fiber-filled plastics	6
3.2 Dimensioning	7
4. RESULTS	8
4.1 Static Test	9
4.2 Dynamic Test	17
5. CONCLUSIONS AND RECOMMENDATIONS	23
6. REFERENCES	25
DISTRIBUTION LIST	27
REPORT DOCUMENTATION PAGE	37

INTENTIONALLY LEFT BLANK.

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1. Experimental setup for testing candidate fin assemblies.	3
2. High-speed photograph of M735, just after sabot discard, ~9 m downrange from muzzle.	4
3. Static firing test result for the standard M735 aluminum fin.	11
4. Static firing test results for (a) MX-2646 and (b) MXBE-55 compression-molded, fiber-filled, thermoset resins (1.52-mm blades).	12
5. Static firing test result for PEI resin with 40% carbon fiber filler (1.02-mm blades).	14
6. Static firing test result for unfilled PEI resin (1.02-mm blades).	15
7. Static firing test result for MX-4600 compression- molded, fiber-filled, thermoset resin (1.52-mm blades).	16
8. Static firing test result for (a) PAEK resin reinforced with 30% E-glass fibers and (b) unfilled PAEK resin (both had 1.52-mm thick blades).	17
9. (a) High-speed downrange photograph and (b) downrange yaw card imprint of M735 rod launched with MX-4600 fins.	19
10. High-speed downrange photograph (~ 30 m from the muzzle) of an M735 rod launched with a fiber-filled PAEK fin assembly.	20
11. Downrange photograph (edited of debris for clarity, using an image scanner) of an M735 rod launched with SS fins molded into a fiber-filled PAEK hub.	21
12. High-speed photograph of an all-plastic (PAEK) fin assembly on a carrier M735 long rod penetrator.	22

INTENTIONALLY LEFT BLANK.

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1. Test Matrix for Candidate Fin Assemblies	9
2. Assessment of Static Firing Test Results	11
3. Assessment of Dynamic Firing Test Results	18

INTENTIONALLY LEFT BLANK.

1. INTRODUCTION

Unlike full-caliber projectiles that deliver high explosives to the target, sub-caliber long rod projectiles utilize kinetic energy (KE) to impart damage to the target. The more aligned the rod axis is with its velocity vector, the further it will penetrate into the target armor. Hence, stabilizing the penetrator to favor a minimum yaw angle is an important factor in defeating the enemy.

Most KE penetrators maintain flight stability by using near-full-caliber fins that extend from the base end of the projectile. The most common KE fin material is aluminum. A typical aluminum fin thickness for a U.S. Army tank main gun (e.g., 105-mm or 120-mm bore diameter) is about 2–3 mm. The standard aluminum fin is chemically treated to create a 0.05–0.08-mm aluminum oxide (refractory) surface layer (hardcoat), which provides considerable, but not complete, protection from thermal erosion.

Prior to launch, KE fins are buried within the propellant bed of the ammunition cartridge case. After propellant ignition, but before muzzle exit, the fins are exposed to high propellant gas temperature and pressure as well as propellant grain impacts. The relative motion between the propellant grains and the fin creates a thermally abrasive in-bore environment that can remove pieces of the hardcoat. Once the hardcoat has been removed, a series of in-bore events can produce rapid erosion of the exposed aluminum substrate. Bundy, Horst, and Robbins (1990) found evidence that where the hardcoat had been chipped away, heating from propellant combustion appeared to have raised the surface temperature of the underlying aluminum to its boiling point. It was then possible for evaporation and subsequent combustion of aluminum vapor to feed energy back to the surface, thus accelerating the "burning" process in width and depth along the fin. In fact, aluminum fin blades that were left uncoated were entirely consumed in a matter of milliseconds when the fin assembly was held at the end of the igniter tube (in close proximity to its initial position in a normal launch) during propellant combustion.

Furthermore, where in-bore erosion has taken place, the aluminum fin is left vulnerable to additional out-of-bore erosion from aerodynamic heating as it travels downrange, particularly for high velocity, long time-of-flight rounds. Not only will the loss of fin surface area reduce stability, it will reduce accuracy because it does not occur symmetrically on each fin blade.

To prevent the erosion of fin surface area, the U.S. Army has been exploring the use of thermal coatings (e.g. Garner 1996) and substitute fin materials, such as steel, to augment or replace hardcoated aluminum. Although an all-steel fin assembly will not incur in-bore damage (Bundy, Horst and Robbins 1990), the weight penalty for replacing aluminum with steel is a notable disadvantage. A compromise solution, examined here, is to use a steel fin in a lightweight plastic fin hub. However, the primary focus of this report is to examine all-plastic fin alternatives.

In spite of plastic's low melting temperature, it is a reasonable material for fin applications because the in-bore heating time is so brief, and the thermal conductivity is so low that only a thin layer of plastic is eroded while it is in bore. Furthermore, unlike aluminum, when plastic burns in bore, the energy released does not add significantly to subsequent fin surface heating. However, as the test results will show, thermal loads are not the only concern with an all-plastic, steel-in-plastic, or fiber-in-plastic fin assembly. If the projectile exits the muzzle at a nonzero yaw angle with respect to the reverse muzzle gas flow (as is common), the fins will encounter asymmetric dynamic pressure loads. The strength and toughness of plastics is then an issue as to whether or not the part will fail in its transition to free flight. The results presented here document some of the successes and failures, both thermally and mechanically, of plastic fins on long rod penetrators.

2. TEST AND EVALUATION PROCESS

2.1 Static Firing

Candidate fin assemblies were tested by attaching them to the end of a standard (bayonet-type) igniter tube extending from a 120-mm combustible cartridge case (stub) base, Figure 1. In this configuration,

the fin assembly remains in the gun chamber during and after the firing event. Normal (automatic) ejection of the stub base after firing is replaced by manual ejection, to reduce the risk of accidentally damaging the test fin during extraction from the gun chamber. As indicated, essentially all of the propellant (in either gas or solid phase form) must pass by the stationary fin assembly in the leading-to-trailing edge direction. The fins are thus exposed to more of the abrasive action of the two-phase (propellant gas and solid grain) flow than they would be if they were attached to the end of the projectile, moving down-bore along with the propellant. Nevertheless, subjecting the fins to thermal conditions that are more extreme than those incurred in a conventional launch provides a rigorous test for evaluating the in-bore success or failure of candidate fin coatings and materials.




Figure 1. Experimental setup for testing candidate fin assemblies.

The projectile fired in the static fin test configuration is a standard slug round with a portion of its tail boom removed to provide space for the fin assembly attached to the end of the primer tube.* The propellant used was granular JA2; the amount was determined from interior ballistics modeling to be that needed to launch the modified slug at the

* Note, after launch, the flight performance of the slug, with its shortened tail boom, is not of interest.

same muzzle velocity as a standard M829A1 120-mm projectile.* Inspection of the post-fired fin was limited to a visual (including microscopic) assessment of the fin surface condition (e.g., breakage, warping, melting, etc.) and a measurement of blade thickness, before vs. after firing, to determine the amount of erosion.

2.2 Dynamic Firing

Based on the static test results, several of the more "successful" alternative fin designs were selected for dynamic (normal launch) testing. An M735 105-mm KE projectile, shown entering free flight in Figure 2, was chosen as the test-bed projectile for carrying the candidate fin assembly downrange. The basis for choosing a 105-mm carrier projectile, as opposed to a 120-mm projectile, was economics: the M735 being less expensive than a comparable 120-mm round.




Figure 2. High-speed photograph of M735, just after sabot discard, ~9 m downrange from muzzle.

* Calculations were performed by Ronald Anderson, Propulsion and Fight Division, U.S. Army Research Laboratory, using the IBHVG2 interior ballistics code.

Whereas the static test exposed the fins to extreme thermal conditions, this phase of the test subjected the fins to realistic mechanical loads, arising from launch acceleration and exposure to uneven muzzle exit pressure. Post-firing assessment of the candidate fin performance was based on muzzle exit radiographs, high-speed free-flight photographs (e.g., Figure 2), downrange yaw cards, and a target impact cloth. In some cases (when the fins failed), it was possible to obtain visual and microscopic (using a scanning electron microscope [SEM]) inspection of post-launched fin pieces found on the ground near the muzzle.

3. COMPOSITION AND DESIGN

3.1 Materials

In this investigation, all of the candidate fin assemblies (hub and blades) were composed either totally or substantially from organic materials. Fin fabrication was done at Los Alamos National Laboratory (LANL), under contract to what is now the Weapons and Materials Research Directorate (WMRD) of the Army Research Laboratory (ARL). In addition, LANL contributed some novel fin lay-up designs, including the injection molding of steel fins in a plastic hub.*

Three families of high-temperature plastics were examined: polyketones, polyimides, and phenolics. Fins were made from these resins with and without fiber fillers, which are added to change the strength and toughness of the overall plastic part. In general, there are advantages and disadvantages to fiber reinforcing of the fin. For example, a thin fin made from unfilled resin may be tough enough to absorb—without breaking (through flexing, bending, and stretching)—the short duration in-bore stresses created by propellant grain impacts, but it may flex beyond its elastic limit when subjected to the longer duration out-of-bore stresses created by uneven muzzle exit pressures. Adding chopped fibers to the injected resin to strengthen it against asymmetric muzzle exhaust flow will also increase its brittleness, in some cases, to the extent that in-bore propellant grain impacts may chip a thin fiber-

* Collin Sadler and Larry Ebaugh from LANL were responsible for the design and fabrication of this type of fin assembly.

filled blade. Filling the resin with longer fibers (e.g., by hand laying a broad cloth into the mold prior to processing) may increase the strength of a thin blade to the point where it no longer chips in bore or breaks out of bore, but with this solution, the simple, inexpensive process of injection molding the fin is no longer possible.

Since production cost is ultimately an important issue, we will henceforth separate the description of fin materials into those that can be injection-molded vs. those that require a hand lay-up step, followed by compression molding. In general, the injection-molded fins were made from either unfilled or short fiber-filled resins. The compression-molded fins were made from resins containing longer fibers that were actually part of a continuous fabric. (The design involving steel fins in a plastic hub was grouped with the injection-molded fins because the hand work was minimal prior to injection molding the hub.)

3.1.1 Short fiber-filled and unfilled plastics In this group, one polyimide and two types of polyketones were tested. In particular, the materials selected for injection molding were a polyetherimide (PEI) from General Electric Co., a polyetheretherketone (PEEK) from ICI, and a polyaryletherketone (PAEK) from BASF Corp. In addition to fabricating unfilled fin assemblies from these three thermoplastic materials, several PEI and PEEK fins were 40% filled with chopped carbon fibers to increase their strength, while some PAEK fins were 30% filled with short strands of E-glass for the same purpose. Lastly, a fin assembly was made by hand laying stainless steel (SS) fin blades into an injection mold. The SS fin hub was created by injecting a PAEK resin, with 30% short fiberglass filler, around fin tabs protruding from the root of the SS blades into the mold's fin hub cavity.

3.1.2 Long fiber-filled plastics Rather than laying a dry fabric into the mold and (hopefully) injecting resin through the fabric, it is common practice to use a fabric that is already preimpregnated with the resin (prepreg). The prepreged fabric is folded into the shape of the fin and then compression molded into the final part.*

* Note, the prepreged fabric will not harden until it is cured in the compression mold at an elevated temperature.

The materials selected for the compression molded fins were chosen from ICI's Fiberite line of ablative broad goods, used in the aerospace industry. In particular, the Fiberite materials that were tested included MX-4600 (a polyamide-modified phenolic resin with ~10- μ m diameter E-glass fiber reinforcement), MX-2646 (a polyamide-modified phenolic resin with ~10- μ m diameter silica fiber reinforcement), and MXBE-55 (an elastomeric-modified phenolic resin with hollow E-glass fiber reinforcement, ~10- μ m diameter). All three Fiberite materials are thermosets. In general, thermoset materials are less flexible than thermoplastics because thermosets contain chemical bonds between polymers (crosslinks) that thermoplastics do not. These crosslinks prevent thermosets from melting and flowing the way thermoplastics can. Note, polyamide and elastomeric modifiers are added to the phenolic resin to increase flexibility/toughness of the composite fin assembly.

3.2 Dimensioning

In addition to differences in composition, strength can also be changed by varying the thickness of the fin blades. Two fin thicknesses were examined: 1.02 mm (0.040 in) and 1.52 mm (0.060 in). For comparison, the aluminum fin on the M735 KE projectile is 3.18 mm (0.125 in) thick at the base of the fin, where it joins to the hub, and 2.03 mm (0.080 in) thick at the tip of the fin. The rationale for selecting plastic fin thickness that were less than the standard aluminum fin was to begin with the thinnest conceivable fin (saving the most weight and aerodynamic drag), then, if necessary to increase fin strength, open up the mold (an irreversible step). However, due to unforeseen budget cutbacks in this project, the strategy of progressing from thin to thicker fins was never completed beyond the second mold iteration, 1.52 mm (0.060 in), which was still roughly one-half the typical aluminum fin thickness. The test matrix for materials and dimensions is summarized in Table 1.

Table 1. Test Matrix for Candidate Fin Assemblies

Injection Molded		Compression Molded
Unfilled Resin	Short Fiber-Filled Resin	Long Fiber Prepreg
PEI hub and blades (1.02 mm thick)	PEI, reinforced with 6.4-mm long carbon fibers in the hub and blades (1.02 mm thick)	MX-4600 (polyamide-modified phenolic), reinforced with a glass fiber broadcloth in hub and blades (1.52 mm thick)
PAEK hub and blades (1.02 and 1.52 mm thick)	PEEK, reinforced with 6.4-mm long carbon fibers in hub and blades (1.02 mm thick)	MX-2646 (polyamide-modified phenolic), reinforced with a silica fiber broadcloth in hub and blades (1.52 mm thick)
	PAEK, reinforced with 6.4-mm long glass fibers in hub and blades (1.02 and 1.52 mm thick)	MXBE-55 (elastomeric-modified phenolic), reinforced with a glass fiber broadcloth in hub and blades (1.52 mm thick)
	PAEK, reinforced with 6.4-mm long glass fibers in hub, and SS blades (1.52 mm thick)	

4. RESULTS

Before discussing each test case, a brief description of how plastics react to heat (Fire 1991) will aid in understanding the results. Plastics are essentially organic compounds consisting primarily of hydrogen, carbon, and in lesser quantity—oxygen, as well as trace amounts of various other elements that can bond covalently. Plastic is formed from the repeated covalent bonding of small molecular units (monomers) into long molecular chains (polymers); additives can be mixed with the

polymers to give the plastic a variety of special properties (e.g., fibers can be added for strength and elastomers can be added for toughness).

When a plastic is heated, the kinetic energy of the molecules can increase to the point where covalent bonds are broken, and simpler, smaller compounds are thus formed. As more heat is added, the breakdown continues until the compounds formed are light enough and active enough to exit the solid as a gas. The source of heat that vaporizes the solid plastic also heats the vapors emitted and thus breaks them down into free radicals of hydrogen, hydrocarbons, and other free radical components of the original polymer. (The heat-induced breaking of covalent bonds in the solid and in the vapor is referred to as pyrolysis.) It is the reaction of hydrogen and hydrocarbon free radicals with oxygen free radicals (pyrolyzed from the original plastic or from some other source in the fire) that releases heat—the heat of combustion—(some of which is in the form of light, creating a visible flame); this is the culminating step in the burning of plastic. If there is insufficient oxygen in the combustion mixture, the burning will be incomplete and will generate free carbon, leaving a telltale black residue on any unburned solid.

If the plastic is a so-called thermoplastic, heat can cause melting and flow before substantial pyrolysis can take place. Consequently, erosion can result from melt removal by "gas wash" over the surface. On the other hand, if the plastic is a thermoset material, it will not undergo melting prior to breaking down into vapor products. In this case, erosion is simply due to evaporation. However, if a solid component accompanies the hot gases, the plastic can also be eroded by chipping, especially for the less flexible thermoset plastics.

4.1 Static Test

In general, whether the fin is a thermoplastic or a thermoset, the in-bore heating time is so brief and the thermal conductivity so low that there is not sufficient time for an appreciable loss of plastic due to thermal ablation (melt removal or evaporation). Typically, 0.05–0.15 mm (0.002–0.006 in) of plastic was removed from exposed surfaces (e.g., hub and blades) during the combustion process in the static fin test. In

comparison, this could amount to 10–20% of the 1.52-mm blade thickness. However, there was one exception where thermal erosion of a compression molded fin was severe, exceeding 50%, as will be discussed.

Outcomes from the static fin test can be grouped as follows. The post-fired fins were either: (1) significantly eroded; (2) fractured (chipped); (3) warped; or (4) virtually undamaged, with the exception of a fairly uniform, but minor degree of ablation. Table 2 summarizes the results; the standard aluminum fin is included for comparison.

Table 2. Assessment of Static Firing Test Results

Eroded	Fractured	Warped	No Significant Damage
M735 aluminum fin (Figure 3)	MXBE-55 (Figure 4(b))	PEI, unfilled hub and blades, 1.02 mm thick (Figure 6)	MX-4600 (Figure 7)
MX-2646 (Figure 4(a))	PEI, fiber-filled hub and blades, 1.02 mm thick (Figure 5)	PAEK, fiber-filled hub and blades, 1.02 mm thick (like Figure 6)	PAEK, both unfilled and fiber-filled hub and blades, 1.52 mm thick (Figure 8)
	PEEK, fiber-filled hub and blades, 1.02 mm thick (like Figure 5)		PAEK, fiber-filled hub with SS blades

As Table 2 conveys, two of the statically tested fins incurred erosion damage, one of them being the standard aluminum fin. As reported by Bundy, Horst, and Robbins (1990), and shown in Figure 3, erosion of the aluminum fin is most severe at the leading edge, receding ~1.0 mm. A degree of nonuniformity can also be seen along the fin edge, varying from one blade to the next. The streak-like patterns extending downstream from the fin edge are deposits of Al_2O_3 , resulting from the vaporization and subsequent oxidation of the aluminum substrate at the leading edge.





Figure 3. Static firing test result for the standard M735 aluminum fin.

Erosion of the compression-molded MX-2646 fin, Figure 4(a), was far worse than shown in Figure 3 for the aluminum fin.* Roughly 50% of the fin height was eroded (erosion also occurred in the width of the fin, perpendicular to the plane of view). It appears, note micrograph inset, that relatively large pieces of the silica crossweave were extricated by the combustion event, leaving voids in the blade surface and increasing exposure of the unreinforced phenolic to the two-phase flow. It is likely that the exposed phenolic matrix was simply chipped away by propellant grain impacts. Where silica fibers were exposed, there was evidence of fiber melting and coalescing at some of the fiber rod ends. In addition, small ($< 1 \mu\text{m}$ in size) whisker-like extensions were found on the silica fibers; they are believed to be SiC crystals that were formed during the pyrolysis process.

* Note, in the static fin test for compression molded fins, three different thermoset resins were tested simultaneously by pinching the root of each blade into a multi-jawed steel collet, which was attached to the end of the igniter tube, Figure 1.



55 Figure 4. Static firing test results for (a) MX-2646 and (b) MXBE-compression-molded, fiber-filled, thermoset resins (1.52-mm blades).

The compression-molded MXBE-55 fin showed less erosion, Figure 4(b), than the MX-2646 fin (Figure 4(a)), but is probably unacceptable as a fin material since it fractured at the blade-collet junction. It is speculated that the hollow glass fibers did not add sufficient strength, nor the elastomer sufficient toughness, to prevent large-scale mechanical failure. Even though melted E-glass fibers were found on the blade surface, fiber bundles appeared to remain within the matrix, impeding erosion longer in this composite than in that of Figure 4(a). The fin width diminished by ~0.05 mm on each side, the equivalent of perhaps four to five layers of 10-μm fibers.

Some indication of the fin surface temperature can be gained from the test results noted thus far. On the conventional hardcoated aluminum fin (Figure 3), the vaporization of aluminum at the leading edge indicates a temperature near 2,300° C. For the compression-molded plastic fins, melting of the silica fibers indicates the surface temperature of the MX-2646 blade exceeded 1,900° C. Melting of E-glass in the MXBE-55 fin suggests the surface temperature was at least 1300° C. One might think that the thermoset plastics, being nonheat conductive compared to aluminum, would retain a higher surface temperature than aluminum. However, when the fiber reinforcement reaches its melting point (m.p.), the two-phase flow can extract heat by removing the molten fibers and surrounding pyrolyzed phenolic, thus limiting the surface temperature rise. It is speculated that a similar ablative heat removal process begins to occur with molten aluminum, but the near-surface exothermic oxidation of small ablating aluminum droplets quickly raises the blade surface temperature to its boiling point.

Another fin material that fractured in the static test was injection-molded PEI, with carbon fiber reinforcement in the hub and (1.02-mm thick) blades, Figure 5. The appearance of rather sharp-edged fin remnants, where the root of the blade joins the hub, implies that although PEI is a thermoplastic, the total loss of all fin blades is probably not due to melting for the most part. Rather, blade loss is most likely caused by chipping of a thermally eroded (thinned) fin. In fact, thickness measurements of the remaining blade fragments revealed that roughly 0.15 mm of material was removed from each side of the blade. This surface regression is roughly three times the level noted for the compression molded fins, and it leaves the remaining ~ 0.7-mm thick fin susceptible to chipping.

Finally, as recorded in Table 2, the 1.02-mm injection-molded PEEK fins, with carbon fiber filler, also fractured in the static test. The reduction in blade thickness was again near 0.15 mm per side, and the fin loss was complete, like that shown in Figure 5.




Figure 5. Static firing test result for PEI resin with 40% carbon fiber filler (1.02-mm blades).

Even though the loss of thermoplastic material was about the same for the unfilled PEI as for the fiber-filled PEI, ~ 0.15 mm per side, the unfilled resin is tough enough to resist fracture from propellant grain impacts, Figure 6. However, the fin blades were left warped by the static heating event. Apparently, the remaining blade material, ~ 0.7 mm thick, absorbed enough heat to be stressed beyond its elastic limit by thermal softening. Likewise, a similar level of heating and erosion left the injection-molded, fiber-filled, 1.02-mm PAEK fins warped, looking like those of Figure 6.

In general, the fiber-filled or unfilled thermoplastic resins, PEI, PEEK, and PAEK, which have melting points near 350°C , all showed a loss of blade thickness that was two to three times higher than the MXBE-55 thermoset resin with E-glass fibers (m.p. 1316°C). The apparent inverse correlation between depth of erosion and m.p. of the resin, or fiber, may imply that the onset of ablation is determined by the lowest m.p. in the composite, whether that is in the matrix or in the fiber.




Figure 6. Static firing test result for unfilled PEI resin (1.02-mm blades).

There were four fins materials that survived the static heating test with virtually no damage. They were the MX-4600 compression-molded blade (1.52 mm thick), the unfilled and short fiber-filled PAEK injection molded fin (1.52 mm thick), and, as expected, the 1.52-mm SS fins in a fiber-filled PAEK hub.

Figure 7 shows the post-heated MX-4600 blade. The SEM micrograph reveals melted and coalesced E-glass fibers separating from the underlying reinforcement. Thickness measurements indicate that ~ 0.07 mm of the glass and resin matrix was eroded from each side. Unlike the MXBE-55 fin, the 10- μ m glass fibers in the MX-4600 blade were solid, not hollow; this, in conjunction with a difference in modifiers, increased the strength of the blade, preventing fin damage like that which occurred in Figure 4(b). It is worth noting that the MX-2646 fin has the same resin and modifier as MX-4600—but different fibers (silica vs. E-glass)—yet, the MX-2646 fin failed catastrophically (Figure 4(a) in comparison to Figure 7).




Figure 7. Static firing test result for MX-4600 compression-molded, fiber-filled, thermoset resin (1.52-mm blades).

Increasing the blade thickness of the thermoplastic PAEK resin to 1.52 mm substantially improved the results (Figures 8(a) and (b) [with and without fiber filler, respectively] compared with Figure 6). As shown, there was virtually no damage to either fin assembly after the static heating test. Once again, ~ 0.15 mm of composite material was thermally eroded from each side of the blades in Figure 8, leaving a fin thickness of ~ 1.2 mm. Apparently, the added 0.5 mm of fin width prevented thermal softening from warping the blades as it did in Figure 6. Even though the amount of material removed from each blade was about the same, there appears to be a slightly heavier layer of (darker colored) carbonaceous char (indicating less available oxygen for burning) on the fin with E-glass filler (Figure 8(a)) compared to the fin without filler (Figure 8(b)).

The only candidate fin design yet to be discussed from Table 2 is the SS blades in the fiber-reinforced PAEK hub. As expected, the SS blades were undamaged by the two-phase flow, and the 0.15 mm recession of the PAEK hub radius was inconsequential.

Of the four fin materials that were virtually undamaged by the static firing test, the lightest was the unfilled PAEK fin assembly (hub and blades) at 70 g. The filled PAEK was slightly heavier, 75 g, followed by the MX-4600, 110 g. The SS blades in a fiber-filled PAEK hub were

the heaviest of all the designs, at 215 g, heavier than the conventional aluminum M735 fin assembly, 175 g.




Figure 8. Static firing test result for (a) PAEK resin reinforced with 30% E-glass fibers and (b) unfilled PAEK resin (both had 1.52-mm-thick blades).

4.2 Dynamic Test

If the fin failed thermally or mechanically in the static fin test, that design was not among those included in the dynamic test. Hence, only the fourth column of Table 2 was examined in this phase.

It has been noted that the dynamic test phase is not as thermally challenging to the candidate fin assemblies as the static fin test. Thus, it was not expected, nor did it occur, that any of the fins that survived the static test failed the dynamic test due to temperature-related damage. On the other hand, the dynamic test exposed the fins for the first time to realistic launch accelerations and uneven muzzle exit pressures; hence, new forces were present that could cause the fins to fail mechanically. Table 3 summarizes the results.

Table 3. Assessment of Dynamic Firing Test Results

Catastrophic Failure	Borderline Failure	Occasional Success
Compression-molded MX-4600 hub and blades	Injection-molded, fiber filled PAEK hub and blades	Injection-molded, unfilled PAEK hub and blades
		Injection-molded, fiber-filled PAEK hub with SS blades

As indicated by the column headings in Table 3, there were no unequivocal successes among the fin designs tried. However, there were occasions when individual fin assemblies flew downrange with little or no apparent damage. Before discussing the occasional successes, the unsuccessful designs are discussed.

One of the most complete failures in the dynamic firing test was the compression-molded MX-4600 fin assembly, Figure 9. In spite of the static firing success of this polyamide-modified phenolic, with glass fiber broad cloth reinforcement, the broad cloth lay-up delaminated and was shred into hundreds of tiny pieces after it left the muzzle. One explanation for the failure is that high-pressure propellant gases entered into the interstitial cavities and voids between the fibers and resin while the assembly remained in-bore, but did not escape fast enough, once out-of-bore, to avoid exploding the part. Evidence that the failure occurred out of bore was based on the fact that only a small fraction of the fragments showed signs of in-bore exposure to high temperatures (i.e., melted or charred surface fibers).

In Figure 9 the rod is flying downrange with a yaw angle of $\sim 5^\circ$ at 5–6 m from the muzzle. Although this is not an unusually large yaw angle at this location (e.g., it is similar in size to that shown in Figure 2 for the standard M735), a fraction of a second later, at 41 m from the muzzle, the yaw angle has increased to at least 45° . This unacceptably high angle, shows by counter example, how important fins are to stabilizing the rod and keeping the yaw angle small.




Figure 9. (a) High-speed downrange photograph, and (b) downrange yaw card imprint of M735 rod launched with MX-4600 fins

The fin assembly fabricated by injection molding PAEK, containing 30% short glass fibers, was a borderline failure because in no cases did it enter free flight without some fin damage, like that shown in Figure 10. It is speculated that if the KE rod has some nonzero angle of attack with respect to the reverse muzzle exhaust flow, which is almost certain to be the case, then the dynamic pressure from this flow can bend the fin blades beyond their yield point. This would explain the large number of broken fin tips found on the ground downrange from the muzzle, one of which is shown in Figure 10. The SEM micrograph of the fin tip surface indicates that the blade surface is softened by the in-bore transient heating. It appears that when propellant grain fragments hit this soft layer they leave crater-like imprints. Flat-bottomed craters imply that the plastic is not thermally softened, to the point of being inelastic, below a certain depth, in this case ~ 0.03 mm. Thickness measurements of the fin fragments revealed that ~ 0.05 mm of surface material was eroded from each side of the blades, this is about one-third the level of erosion that occurred in the static firing test.

Even though the loss of fin surface area was not complete in Figure 10, it was significant to the extent that it would be unacceptable in terms of the effect it has on destabilizing the round, which is borne out by the high yaw angle of $\sim 15^\circ$ near 30 m from the muzzle.




Figure 10. High-speed downrange photograph (~ 30 m from the muzzle) of an M735 rod launched with a fiber-filled PAEK fin assembly.

The SS-plastic fin design was occasionally successful, but when it failed, e.g., Figure 11, the loss of blades was as complete as that of Figure 9. The appearance of curled and twisted SS blades in Figure 11 implies that the reverse muzzle exhaust flow impinged on the blades from an oblique angle (note, the yaw angle of the rod in Figure 11 was about 3°), forcing the blade tips to curl over and eventually twisting them out of the plastic fin hub.

The tracer cavity plug, shown in Figure 11, is utilized as a precaution to prevent in-bore gases from filling this cavity and not escaping fast enough, after muzzle exit, to avoid exploding the fin hub.




Figure 11. Downrange photograph (edited of debris for clarity, using an image scanner) of an M735 rod launched with SS fins molded into a fiber-filled PAEK hub.

The unfilled PAEK fins gave the most promising results. Out of two fin assemblies tested, high-speed photographs and yaw card imprints showed one assembly lost two of six fin tips due to fracture, with the remaining four tips exhibiting extreme flexure. However, the other PAEK fin assembly flew downrange essentially undamaged, as shown in Figure 12. The yaw cards, at 41 m and 53 m from the muzzle, show that all fins are full span and none are chipped. There appears to be a slight flexing of some blades as indicated by the small curvature in the yaw card silhouette. (It is presumed that the blades are flexing because no permanent warping was observed in the more intense thermal environment of static firing.)

It has been speculated that the initial yaw angle relative to the reverse muzzle exhaust flow contributes to the loss of fins, due to bending of the blades by asymmetric dynamic pressure loads. Unlike Figures 2, 9, and 11, the yaw angle at ~ 7 m from the muzzle in Figure 12 is small, $< 1^\circ$, and was probably small at muzzle exit. This

would suggest that asymmetric dynamic pressure loads were probably small at muzzle exit, which could help explain why there was not only no fin chipping, but very little fin flexing. Furthermore, the continued low yaw angles at 41 m and 53 m from the muzzle (indicated by the near circular yaw card impacts) demonstrates that the fin is serving to maintain flight stability of the rod.




Figure 12. High-speed photograph of an all-plastic (PAEK) fin assembly on a carrier M735 long rod penetrator.

5. CONCLUSIONS AND RECOMMENDATIONS

This report documents a multiyear study of plastic fins for use on long rod KE penetrators. An M735, a 105-mm round with a muzzle exit velocity of ~ 1600 m/s, was chosen as the carrier projectile for test comparisons. Several types of plastics were evaluated, from specialized compression-molded broad clothes, preimpregnated with thermoset resins (like those used in the aerospace industry), to more general purpose injection-molded engineering-type thermoplastics (such as PEEK).

The long-range plan of the program was to start with thin molded fins, roughly one-third the blade thickness of the standard aluminum fin, then open up the mold (an irreversible step) if necessary, to increase the blade thickness (strength). However, lack of continuing funds halted the program at the second fin thickness iteration, which was still only one-half the standard aluminum fin thickness. Nevertheless, a great deal was learned about the use of plastics for this application.

Nine candidate fin materials were chosen for testing. Of these nine, only four performed better than aluminum in resisting in-bore damage from the two-phase propellant flow (as determined in static fire testing). These four then underwent further testing by launching them on the carrier M735 rod. Of the four, two were occasionally successful in stabilizing the rod, with no appreciable thermal erosion or mechanical damage (bent or chipped fins).

One of the two occasionally successful fins had SS blades in a plastic hub. However, further development of this design is not recommended since there is little room for substantial improvement in the design without increasing the fin weight, which is already heavier than the baseline (M735) aluminum fin.

On the other hand, the other occasionally successful design, an all-plastic fin assembly (injection-molded using an unfilled thermoplastic resin—PAEK from BASF Corp.) has considerable latitude for improvement without exceeding the drag and weight penalties of the standard aluminum fin. For example, it is believed that going from the

current 1.52 mm straight-cut PAEK fin to a 2–3 mm tapered-cut (from tip to root) PAEK fin, would provide the necessary margin of safety to ensure a damage-free transition to free flight. Since such a shape is roughly the same as the baseline aluminum fin there would not be any benefit from reduced drag, but the PAEK fin would offer a weight savings: weighting only 50–60% as much as its aluminum counterpart. (A fin weight reduction is advantage to improving flight stability because it moves the center of gravity forward, which increases the stabilizing moment.) Most importantly, the test results showed that thermal erosion for such a plastic fin would be far less—and more uniform—than for a comparable aluminum fin. For example, from the static firing test, it was shown that the PAEK fin had a uniform erosion of ~ 0.15 mm, whereas, for the aluminum fin, the leading edge regression was ~ 1 mm, and it varied from blade to blade. Nonuniform erosion creates the adverse effect of increasing ammunition dispersion.

In general, this study proved that a thin (one-half as thick as the standard 2–3-mm aluminum fin), lightweight (40% as heavy as the standard 175-g fin) all-plastic (PAEK) fin assembly can stabilize a long rod (M735) KE penetrator with virtually no in-bore thermal erosion (~ 0.05 mm surface regression). However, to prevent out-of-bore mechanical fin damage (bent or chipped blades) it appears that the rod must exit the muzzle at small yaw angles. To enlarge the tolerance to muzzle exit angles requires thickening the PAEK fin blade (as discussed above). Hence, the critical factor in plastic fin design is not thermal erosion, as one might expect, but rather, it is the ability to flex without breaking in the reverse muzzle exhaust flow. This would indicate that if other polymers are considered for fin applications in the future, the sought after characteristics would be for more flexibility, elasticity, or rubber-like qualities than PAEK.

6. REFERENCES

Bundy, M. L., A. W. Horst, and F. W. Robbins. "Effects of In-bore Heating on Projectile Fins." BRL-TR-3106, U.S. Ballistic Research Laboratory, Aberdeen Proving Ground, MD, June 1990.

Fire, F. L. Combustibility of Plastics. Van Nostrand Reinhold, New York, 1991.

Garner, J. M. "Fin Protection via Combustible Coatings." ARL-MR-316, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, June 1996.

INTENTIONALLY LEFT BLANK

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFO CTR ATTN DTIC DDA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDQ ATTN DENNIS SCHMIDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	US MILITARY ACADEMY MATH SCI CTR OF EXCELLENCE DEPT OF MATHEMATICAL SCI ATTN MDN A MAJ DON ENGEN THAYER HALL WEST POINT NY 10996-1786
1	DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CS AL TP 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CS AL TA 2800 POWDER MILL RD ADELPHI MD 20783-1145
3	DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1145
	<u>ABERDEEN PROVING GROUND</u>
2	DIR USARL ATTN AMSRL CI LP (305)

NO. OF COPIES	ORGANIZATION
4	COMMANDER US ARMY ARMOR CENTER ATTN ATSB CD ATSB SBE ORSA FORT KNOX KY 40121
2	PEO FOR ARMAMENTS ATTN SFAE AR SFAE AR D PICATINNY ARSENAL NJ 07806-5000
1	HEADQUARTERS US ARMY MATERIEL CMD ATTN AMCICP AD M FISETTE 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	US ARMY BMDS CMD ADVANCED TECHLGY CTR PO BOX 1500 HUNTSVILLE AL 35807-3801
7	COMMANDER TANK MAIN ARMAMENT SYS ATTN SFAE AR TMA V ROSAMILIA R BILLINGTON W KATZ R JOINSON C ROLLER E KOPACZ K RUBEN PICATINNY ARSENAL NJ 07806-5000
5	COMMANDER US ARMY ARDEC ATTN AMSTA AR AE AMSTA AR FSF GD K PFLEGER AMSTA AR FSF BV V GALGANO C GONZALES C LANGEN PICATINNY ARSENAL NJ 07806-5000

NO. OF COPIES	ORGANIZATION
4	COMMANDER US ARMY ARDEC ATTN AMSTA AR CCH V C MANDALA E FENNELL A GOWARTY J PETTY PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC ATTN AMSTA AR AEE B S BERNSTEIN PICATINNY ARSENAL NJ 07806-5000
4	COMMANDER US ARMY ARDEC ATTN AMSTA AR QAT A L DULISSI C PATEL R ROESER G MAGISTRO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC ATTN AMSTA AR AEE J LANNON PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC ATTN AMSTA AR ATE A STAN KAHN PICATINNY ARSENAL NJ 07806-5000
5	COMMANDER US ARMY ARDEC ATTN SFAE FAS AF COL D NAPOLIELLO L YUNG T KURIATA E DELCOCO H TRAN PICATINNY ARSENAL NJ 07806-5000

NO. OF
COPIES ORGANIZATION

2 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR FSF BD
 R MEENAN
 J DELABAR
 PICATINNY ARSENAL NJ
 07806-5000

2 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR FSS A
 L MUND
 L PINDER
 PICATINNY ARSENAL NJ
 07806-5000

2 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR FSS E
 J BROOKS
 M ENNIS
 PICATINNY ARSENAL NJ
 07806-5000

1 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR FSE T GORA
 PICATINNY ARSENAL NJ
 07806-5000

3 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR TD
 R PRICE
 V LINDNER
 C SPINELLI
 PICATINNY ARSENAL NJ
 07806-5000

1 COMMANDER
 US ARMY ARDEC
 ATTN F MCLAUGHLIN
 PICATINNY ARSENAL NJ
 07806-5000

NO. OF
COPIES ORGANIZATION

4 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR FSF T
 T FARINA
 C NG
 J WHYTE
 J GRAU
 PICATINNY ARSENAL NJ
 07806-5000

4 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR CCH T
 S MUSALLI
 P CHRISTIAN
 R CARR
 N KRASNOW
 PICATINNY ARSENAL NJ
 07806-5000

1 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR CCH J DELORENZO
 PICATINNY ARSENAL NJ
 07806-5000

2 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR CC
 J HEDDERICH
 COL EHLIY
 PICATINNY ARSENAL NJ
 07806-5000

1 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR CCH P J LUTZ
 PICATINNY ARSENAL NJ
 07806-5000

2 COMMANDER
 US ARMY ARDEC
 ATTN AMSTA AR FSA M
 D DEMELLA
 F DIORIO
 PICATINNY ARSENAL NJ
 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	COMMANDER US ARMY ARDEC ATTN AMSTA AR FSA A WARNASH B MACHAK PICATINNY ARSENAL NJ 07806-5000
15	DIRECTOR US ARMY ARDEC ATTN AMSTA AR CCB J KEANE J BATTAGLIA J VASILAKIS G PFLEGL G FRIAR P O'HARA M WITHERELL R GAST C A ANDRADE J HAAS A GABRIEL P VOTIS J HIGGINS R HASENBEIN AMSTA AR CCB T S SOPOK BENET LABS WATERVLIET NY 12189
1	COMMANDER US ARMY ARDEC ATTN AMSMC PBM K PROD BASE MODERN ACTY PICATINNY ARSENAL NJ 07806-5000
2	DIRECTOR BENET WEAPONS LABS WATERVLIET NY 12189-4050
1	PROGRAM MANAGER US ARMY TACOM ATTN AMCPM ABMS T DEAN WARREN MI 48092-2498
1	PROGRAM MANAGER US ARMY TACOM ATTN SFAE ASM BV FIGHTING VEHICLE SYSTEMS WARREN MI 48397-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	COMMANDER US ARMY TACOM ATTN SFAE ASM AB SW DR PATTISON MAJ M PADGETT WARREN MI 48397-5000
1	PROGRAM MANAGER ABRAMS TANK SYSTEM ATTN SFAE ASM AB WARREN MI 48397-5000
1	COMMANDANT US ARMY CMD & GEN STAFF COLLEGE FORT LEAVENWORTH KS 66027
1	COMMANDANT US ARMY SPCL WARFARE SCHL ATTN REV AND TRNG LIT DIV FORT BRAGG NC 28307
1	COMMANDER RADFORD ARMY AMMUNITION PLANT ATTN SMCAR QA HI LIB RADFORD VA 24141-0298
1	COMMANDER US ARMY NGIC ATTN AMXST MC 3 220 SEVENTH STREET NE CHARLOTTESVILLE VA 22901-5396
1	COMMANDANT US ARMY ARMOR SCHOOL ATTN ATZK CD MS M FALKOVITCH ARMOR AGENCY FORT KNOX KY 40121-5215
1	DIR OF TRNG & DOCTRINE DEVELOPMENT DOCTRINE DIVISION ATZK TDD G MR POMEY FORT KNOX KY 40121-5000
2	PM AFAS ATTN SFAE ASM AF LTC A ELLIS LTC B ELLIS PICATINNY ARSENAL NJ 07806-5000

NO. OF
COPIES ORGANIZATION

3 OFFICE OF THE PM
M109/AG PALADIN
ATTN SFAE AR HIP
J CARBONE
K HURBAN
S WALL
PICATINNY ARSENAL NJ
07806-5000

1 COMMANDER
USA ARMAMENT MUNTNS & CHEMCL CMD
ATTN AMSMC DSD C J O'DONNELL
ROCK ISLAND IL 61299-6000

1 HQDA
PENTAGON
ATTN SARD TT DR F MILTON
WASHINGTON DC 20310-0103

1 HQDA
PENTAGON
ATTN SARD TR DR R CHAIT
WASHINGTON DC 20310-0103

1 HQDA
PENTAGON
ATTN SARD TR
MS K KOMINOS
WASHINGTON DC 30310-0103

1 DIRECTOR
US ARMY RESEARCH LAB
ATTN AMSRL CP CA D SNIDER
2800 POWDER MILL RD
ADELPHI MD 20783

1 COMMANDER
US ARMY TACOM
ATTN AMSTA JSK S GOODMAN
WARREN MI 48397-5000

1 COMMANDER
ATTN SMCWV QAE Q C HOWD
BLDG 44 WATERVLIET ARSNL
WATERVLIET NY 12189-4050

1 COMMANDER
ATTN SMCWV SPM T MCCLOSKEY
BLDG 25 3 WTRVLT ARSNL
WATERVLIET NY 12189-4050

NO. OF
COPIES ORGANIZATION

1 COMMANDER
WATERVLIET ARSENAL
ATTN SMCWV QA QS K INSCO
WATERVLIET NY 12189-4050

1 COMMANDER
US ARMY BELVOIR RD&E CTR
ATTN STRBE JBC
FORT BELVOIR VA 22060-5606

1 US ARMY COLD REGIONS RSCH &
ENGINEERING LABORATORY
ATTN P DUTTA
72 LYME RD
HANOVER NH 03755

1 DIRECTOR
US ARMY RESEARCH LAB
ATTN AMSRL WT L
D WOODBURY
2800 POWDER MILL RD
ADELPHI MD 20783-1145

2 US ARMY RESEARCH OFFICE
ATTN A CROWSON
J CHANDRA
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

3 COMMANDER
US ARMY MISSILE COMMAND
ATTN AMSMI RD W MCCORKLE
AMSMI RD ST P DOYLE
AMSMI RD ST CN T VANDIVER
REDSTONE ARSENAL AL 35898

3 US ARMY RESEARCH OFFICE
ATTN R SINGLETON
G ANDERSON
K IYER
ENGINEERING SCIENCES DIV
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

2 PROJECT MANAGER
SADARM
PICATINNY ARSENAL NJ
07806-5000

NO. OF COPIES	ORGANIZATION
2	PM TANK MAIN ARM SYS ATTN SFAE AR TMA COL BREGARD K KIMKER PICATINNY ARSENAL NJ 07806-5000
3	PM TANK MAIN ARM SYS ATTN SFAE AR TMA MD R KOWALSKI B HELD B DACEY PICATINNY ARSENAL NJ 07806-5000
2	PEO FIELD ART SYS ATTN SFAE FAS PM D ADAMS T MCWILLIAMS PICATINNY ARSENAL NJ 07806-5000
1	PEO FIELD ART SYS ATTN SFAE FAS PM H GOLDMAN PICATINNY ARSENAL NJ 07806-5000
2	PM AFAS ATTN G DELCOCO J SHIELDS PICATINNY ARSENAL NJ 07806-5000
2	PROGRAM MANAGER GROUND WEAPONS MCRDAC CBGT QUANTICO VA 22134-5000
2	COMMANDER NAVAL SEA SYSTEMS CMD ATTN SEA 62R SEA 64 WASHINGTON DC 20362-5101

NO. OF COPIES	ORGANIZATION
4	COMMANDER NAVAL RSRCH LAB ATTN TECHNICAL LIBRARY CODE 4410 K KAILASANATE J BORIS E ORAN WASHINGTON DC 20375-5000
1	OFFICE OF NAVAL RSRCH ATTN CODE 473 R S MILLER 800 N QUINCY ST ARLINGTON VA 22217-5000
1	OFFICE OF NAVAL TECHLGY ATTN ONT 213 D SIEGEL 800 N QUINCY ST ARLINGTON VA 22217-5000
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN CODE 730 SILVER SPRING MD 20903-5000
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN CODE R 13 R BERNECKER SILVER SPRING MD 20903-5000
7	COMMANDER NAVAL SURFACE WARFARE CTR ATTN T C SMITH K RICE S MITCHELL S PETERS J CONSAGA C GOTZMER TECH LIB INDIAN HEAD MD 20640-5000
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN CODE G30 GUNS & MUNITIONS DIV DAHLGREN VA 22448-5000
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN CODE G32 GUNS SYSTEMS DIV DAHLGREN VA 22448-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN CODE G33 T DORAN DAHLGREN VA 22448-5000
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN CODE E23 TECH LIB DAHLGREN VA 22448-5000
2	COMMANDER NAVAL SURFACE WARFARE CTR ATTN CODE G33 DAHLGREN DIV DAHLGREN VA 22448
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN JOSEPH H FRANCIS CODE G30 DAHLGREN VA 22448
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN JOHN FRAYSSE CODE G33 DAHLGREN VA 22448
1	COMMANDER NAVAL SURFACE WARFARE CTR ATTN MARY E LACY CODE D4 17320 DAHLGREN RD DAHLGREN VA 22448
2	COMMANDER NAVAL AIR WARFARE CTR ATTN CODE 388 C F PRICE T BOGGS CHINA LAKE CA 93555-6001
2	COMMANDER NAVAL AIR WARFARE CTR ATTN CODE 3895 T PARR R DERR CHINA LAKE CA 93555-6001
1	COMMANDER NAVAL AIR WARFARE CTR INFORMATION SCIENCE DIV CHINA LAKE CA 93555-6001

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	OFFICE OF NAVAL RESEARCH ATTN YAPA RAJAPAKSE MECH DIV CODE 1132SM ARLINGTON VA 22217
1	NAVAL ORDNANCE STATION ATTN D HOLMES CODE 2011 ADVANCED SYS TECH BR LOUISVILLE KY 40214-5245
2	DAVID TAYLOR RESEARCH CTR ATTN R ROCKWELL W PHYLLAIER BETHESDA MD 20054-5000
1	EXPED WARF DIV N85 ATTN DR FRANK SHOUP 2000 NAVY PENTAGON WASHINGTON DC 20350-2000
1	OFFICE OF NAVAL RESEARCH ATTN MR DAVID SIEGEL 351 800 N QUINCY ST ARLINGTON VA 22217-5660
1	COMMANDER NAVAL SEA SYSTEMS CMD ATTN D LIESE 2531 JEFFERSON DAVIS HWY ARLINGTON VA 22242-5160
1	SDIO TNI PENTAGON ATTN L H CAVENY WASHINGTON DC 20301-7100
1	SDIO DA PENTAGON ATTN E GERRY WASHINGTON DC 21301-7100
2	HQ DNA ATTN D LEWIS A FAHEY 6801 TELEGRAPH RD ALEXANDRIA VA 22310-3398

NO. OF COPIES	ORGANIZATION
2	CPIA JHU ATTN H J HOFFMAN T CHRISTIAN 10630 LITTLE PATUXENT PWY STE 202 COLUMBIA MD 21044-3200
2	NASA LANGLEY RESEARCH CTR ATTN AMSRL VS W ELBER F BARTLETT JR MS 266 HAMPTON VA 23681-0001
1	DEFENSE NUCLEAR AGENCY ATTN DR R ROHR INNOVATIVE CONCEPTS DIV 6801 TELEGRAPH RD ALEXANDRIA VA 22310-3398
1	DEFENSE NUCLEAR AGENCY ATTN LTC JYUJI D HEWITT INNOVATIVE CONCEPTS DIV 6801 TELEGRAPH RD ALEXANDRIA VA 22310-3398
1	DIRECTOR SANDIA NATL LABS ATTN M BAER DEPARTMENT 1512 PO BOX 5800 ALBUQUERQUE NM 87185
1	DIRECTOR SANDIA NATL LABS ATTN R CARLING COMBUSTION RSRCH FACILITY LIVERMORE CA 94551-0469
1	DIRECTOR SANDIA NATL LABS ATTN 8741 G A BENEDITTI PO BOX 969 LIVERMORE CA 94551-0969
2	DIRECTOR LAWRENCE LIVERMORE NATL LABS ATTN L 355 A BUCKINGHAM M FINGER PO BOX 808 LIVERMORE CA 94550-0622

NO. OF COPIES	ORGANIZATION
1	DIRECTOR LOS ALAMOS NATL LAB ATTN T3 D BUTLER PO BOX 1663 LOS ALAMOS NM 87544
1	GENERAL APPLIED SCIENCES LAB ATTN J ERDOS 77 RAYNOR AVE RONKONKAMA NY 11779-6649
1	DIRECTOR LOS ALAMOS NATL LAB ATTN D RABERN MEE 13 MS J 576 PO BOX 1633 LOS ALAMOS NM 87545
1	THE UNIV OF AUSTIN TEXAS ATTN T M KIEHNE INSTITUTE FOR ADVANCED TECHLGY 4030 2 W BRAKER LAND AUSTIN TX 78759-5329
4	PENNSYLVANIA STATE UNIV ATTN V YANG K KUO C MERKLE G SETTLES DEPT OF MECHANICAL ENGRG UNIVERSITY PARK PA 16802-7501
1	PRINCETON COMBUSTION RSRCH LABS INC ATTN N A MESSINA PRINCETON CORPORATE PLAZA 11 DEERPARK DR BLDG IV SUITE 119 MONMOUTH JUNCTION NJ 08852
1	RENSSELAER POLYTECH INST ATTN R B PIPES PRES OFC PITTSBURGH BLDG TROY NY 12180-3590
2	BATTELLE ATTN TWSTIAC V LEVIN 505 KING AVE COLUMBUS OH 43201-2693

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	BATTELLE PNL ATTN MR MARK GARNICH PO BOX 999 RICHLAND WA 99352
1	BATTELLE ATTN C R HARGREAVES 505 KING AVE COLUMBUS OH 43201-2681
1	BATTELLE PNL ATTN M SMITH PO BOX 999 RICHLAND WA 99352
1	AFELM THE RAND CORP ATTN LIBRARY D 1700 MAIN ST SANTA MONICA CA 90401-3297
2	AAI CORPORATION ATTN J FRANKLE D CLEVELAND PO BOX 126 HUNT VALLEY MD 21030-0126
8	ALLIANT TECHSYSTEMS INC ATTN R E TOMPKINS J KENNEDY J BODE C CANDLAND L OSGOOD R BURETTA R BECKER M SWENSON 600 SECOND ST NE HOPKINS MN 55343
1	GENERAL ELECTRIC COMPANY ATTN J MANDZY TACTICAL SYSTEM DEPT 100 PLASTICS AVE PITTSFIELD MA 01201-3698
1	LOCKHEED MARTIN ATTN JIM TALLEY ROOM 1309 LAKESIDE AVE BURLINGTON VT 05401

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	OLIN ORDNANCE ATTN A SAITTA 10101 9TH ST NORTH ST PETERSBURG FL 33716
3	OLIN ORDNANCE ATTN E J KIRSCHKE A F GONZALEZ D W WORTHINGTON PO BOX 222 ST MARKS FL 32355-0222
1	OLIN ORDNANCE ATTN H A MCELROY 10101 9TH ST NORTH ST PETERSBURG FL 33716
1	PHYSICS INTRNATL LIBRARY ATTN H WAYNE WAMPLER PO BOX 5010 SAN LEANDRO CA 94577-0599
3	ROCKWELL INTRNTL ATTN BA08 J FLANAGAN J GRAY R B EDELMAN ROCKETDYNE DIV 6633 CANOGA AVE CANOGA PARK CA 91303-2703
2	ROCKWELL INTRNTL SCIENCE CTR ATTN DR S CHAKRAVARTHY DR S PALANISWAMY 1049 CAMINO DOS RIOS PO BOX 1085 THOUSAND OAKS CA 91360
1	SAIC ATTN M PALMER 2109 AIR PARK RD ALBUQUERQUE NM 87106
1	SOUTHWEST RSRCH INSTITUTE ATTN J P RIEGEL 6220 CULEBRA RD PO DRAWER 28510 SAN ANTONIO TX 78228-0510

NO. OF COPIES	ORGANIZATION
3	THIOKOL CORPORATION ATTN R WILLER R BIDDLE TECH LIB ELKTON DIVISION PO BOX 241 ELKTON MD 21921-0241
4	VERITAY TECHLGY INC ATTN E B FISHER A CRICKENBERGER J BARNES J Z TALLEY PO BOX 305 4845 MILLERSPORT HWY EAST AMHERST NY 14501-0305
1	UNIVERSAL PROPULSION COMPANY ATTN H J MCSPADDEN 25401 NORTH CENTRAL AVE PHOENIX AZ 85027-7837
1	SRI INTERNATIONAL ATTN TECH LIB PROPULSION SCIENCES DIV 333 RAVENWOOD AVE MENLO PARK CA 94025-3493
1	GENERAL DYNAMICS ATTN D BARTLE LAND SYSTEMS DIVISION PO BOX 1901 WARREN MI 48090
1	PM ADVANCED CONCEPTS ATTN R TAYLOR LORAL VOUGHT SYSTEMS PO BOX 650003 MS WT 21 DALLAS TX 76265-0003
2	LORAL VOUGHT SYSTEMS ATTN G JACKSON K COOK 1701 W MARSHALL DR GRAND PRAIRIE TX 75051
2	UNITED DEFENSE LP ATTN P PARA G THOMAS 1107 COLEMAN AVE BOX 367 SAN JOSE CA 95103

NO. OF COPIES	ORGANIZATION
	<u>ABERDEEN PROVING GROUND</u>
2	DIR USAMSAA ATTN AMXSY GA W BROOKS B SIEGEL
1	DIR USAEAC ATTN CSTE EAC CC
2	CDR USA TECOM ATTN AMSTE SI F AMSTE TA R
4	DIR USA ATC ATTN STECS CC PC P DURKIN STECS LI S STECS AS STECS AS H
5	DIR USARL ATTN AMSRL WT P A HORST 390A AMSRL WT PD T ERLINE 390 D HOPKINS 390 S WILKERSON 390 AMSRL WT WB F BRANDON 120

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE December 1996	3. REPORT TYPE AND DATES COVERED Final, 1987-1996		
4. TITLE AND SUBTITLE Plastic Fins for Kinetic Energy (KE) Penetrators		5. FUNDING NUMBERS PR: 1L162618AH80		
6. AUTHOR(S) Mark L. Bundy				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-PB Aberdeen Proving Ground, MD 21005-5066		8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-1267		
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)		10.SPONSORING/MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Most conventional sub-caliber long rod penetrators maintain flight stability by using near-full-caliber hardcoated aluminum fins that extend from the base end of the projectile. Prior to launch, these fins are buried within the propellant bed of the ammunition cartridge case. During launch, the fins are subjected to high propellant gas temperature and pressure, as well as propellant grain impacts. This thermally abrasive in-bore environment can remove pieces of the fin's hardcoat, thus exposing the aluminum substrate to temperatures far beyond its melting point. Thermal erosion of the fin degrades projectile stability and accuracy. Thus, the U.S. Army is exploring more effective thermal coatings and/or substitute fin materials to replace hardcoated aluminum. The use of plastics is one alternative. This report will document some of the successes and failures of plastic fin assemblies on kinetic energy (KE) penetrators. For example, it was found that fins made from some plastics incur less in-bore thermal damage than hardcoated aluminum. On the other hand, it appears that plastic fins, at least relatively thin plastic fins, are susceptible to mechanical failure out of bore if they traverse the reverse muzzle gas flow at all but small yaw angles. Nonetheless, there appears to be design latitude for a plastic fin assembly that would be lighter in weight and more erosion resistant than the current hardcoated aluminum fin.				
14. SUBJECT TERMS plastics, composites, fins, penetrators, in-bore, heating, pyrolysis, melting, evaporation, ablation, erosion			15. NUMBER OF PAGES 41	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-1267 (Bundy) Date of Report December 1996
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)

(DO NOT STAPLE)